

**FAX**

Date 12-5-02

Number of pages including cover sheet 22

TO:

Tatiana Zalukaeva

Phone 703-308-8819

Fax 703-872-4040

FROM: Michael Morgan

Phone (248)948-2021

Fax Phone (248)948-2093

CC:

REMARKS: ☐ Urgent ☒ For your review ☐ Reply ASAP ☐ Please Comment

The information contained in this facsimile message is Privileged and Confidential and Intended for the use of the Intended Recipient named above. If the reader of this message is not the intended Recipient (or the employee or agent responsible to deliver it to the Intended Recipient), you are hereby notified that any dissemination, distribution or copying of this communication is prohibited. If you have received this communication in error, please immediately notify us by collect telephone and return the original message to us at the address above at our expense.

Preliminary Amendment and  
Return Receipt post card  
for 09/830,644  
Filed 5-14-01

## THIS ACKNOWLEDGES:

J047 Rec'd PCT/PTO 27 APR 2001

<input checked="" type="checkbox"/>	Transmittal Form 1390 under 35 USC §371 in triplicate	<input checked="" type="checkbox"/>	Information Disclosure Statement
<input checked="" type="checkbox"/>	PCT Published Application cover sheet only	<input checked="" type="checkbox"/>	Preliminary Amendment 37 CFR
<input type="checkbox"/>	Recordation Form Cover Sheet <u>in triplicate</u>	<input type="checkbox"/>	Statement under 37 CFR § 3.73§1.115
<input checked="" type="checkbox"/>	PTO-1449 Form & Cited Reference(s)	<input type="checkbox"/>	Assignment to BASF
<input checked="" type="checkbox"/>	Cover Page of the Priority Document	<input checked="" type="checkbox"/>	International Search Report
<input type="checkbox"/>	Combined Declaration/Power of Attorney	<input type="checkbox"/>	
<input type="checkbox"/>	Associate Power of Attorney	<input checked="" type="checkbox"/>	PCT/EP99/08063 Application English Translation
<input checked="" type="checkbox"/>	PCT/EP99/08063 Application Original German Text		
<input checked="" type="checkbox"/>	Specification on	52	page(s)
<input checked="" type="checkbox"/>	Claims on	07	page(s)
<input checked="" type="checkbox"/>	Abstract on	01	page(s)
<input type="checkbox"/>	Drawing(s) on	00	page(s)
<input checked="" type="checkbox"/>	Specification on	73	page(s)
<input checked="" type="checkbox"/>	Claims on	09	page(s)
<input checked="" type="checkbox"/>	Abstract on	01	page(s)
<input type="checkbox"/>	Drawing(s) on	00	page(s)

Application No.:

Docket No.:

Filing Date:

Inventor(s):

Attorney(s):

Express Label No.:

IN-5484

Friday, April 27, 2001

Heinz-Peter RINK et al.

X Anne Gerry Sabourin

Mary E. Golota

EK157042270US

09/830694

glycidyl esters of Versatic acid;

(vii) epoxy resin esters of saturated and unsaturated fatty acids;

and

(viii) epoxidized triglycerides of natural oils and esters, and mixtures thereof.

21. (New) A homopolymer or copolymer of claim 2 prepared by homopolymerization or copolymerization of olefinically unsaturated monomers in a Taylor reactor having an external reactor wall located within which there is a concentrically or eccentrically disposed rotor, a reactor floor and a reactor lid, which together define the annular reactor volume, at least one means for metered addition of reactants, and a means for the discharge of product, where the reactor wall and/or the rotor are or is geometrically designed in such a way that the conditions for Taylor vortex flow are met over substantially the entire reactor length in the reactor volume, in such a way that the annular gap broadens in the direction of flow traversal.

22. (New) A process for preparing a homopolymer or copolymer of olefinically unsaturated compounds by free-radical copolymerization in a liquid reaction medium, which comprises using as a reaction medium, reactive diluents for thermally curable multicomponent mixtures.

23. (New) The process as claimed in claim 22, wherein a fraction of the reactive diluents is modified after the copolymerization with olefinically unsaturated compounds, so that the resulting composition is curable by means selected from thermal, actinic light, electron beams and mixtures thereof.

24. (New) The process as claimed in claim 22, wherein a fraction of the reactive diluents is modified after the copolymerization with olefinically

12

unsaturated compounds selected from the group consisting of monomers (A2), (A5) and (A6) and mixtures thereof, and the resulting composition is cured by means selected from thermal, actinic light, electron beams and mixtures thereof.

25. (New) A coating composition comprising the liquid composition of claim 1, cured by means selected from thermal, actinic light, electron beam and mixtures thereof.

26. (New) An adhesive comprising the liquid composition of claim 1 cured by means selected from thermal, actinic light, electron beam and mixtures thereof.

27. (New) A composition selected from the group consisting of coating compositions, sealants, and adhesives, comprising the liquid composition of claim 1 cured by means selected from thermal, actinic light, electron beam and mixtures thereof.

28. (New) A composition selected from the group consisting of coating compositions, sealants and adhesives, comprising the homopolymer or copolymer of claim 2 cured by means selected from thermal, actinic light, electron beam and mixtures thereof.

29. (New) A composition selected from the group consisting of coating compositions, sealants and adhesives, comprising the liquid composition prepared by the method of claim 8, cured by means selected from thermal, actinic light, electron beam and mixtures thereof.

30. (New) A composition selected from the group consisting of coating compositions, sealants and adhesives comprising the homopolymer or copolymer prepared by the method of claim 21, cured by means selected from thermal, actinic light, electron beam and mixtures thereof.